



中国认可
国际互认
检测
TESTING
CNAS L1538

Test Report

TEST ITEMS

Test for *in vitro* cytotoxicity (MTT cytotoxicity test)

TEST ARTICLE

Medical endoscope insertion tube
<Production date: 2023.7.1; Lot : 230701>

IDENTIFICATION №

230720

MANUFACTURER

Changzhou Yanshun Optronics & Technology Co., Ltd.
<Address: No. 2965 Longcheng Rd. Luoxi Town Xinbei District ChangZhou>

SPONSOR

Changzhou Yanshun Optronics & Technology Co., Ltd.
<Address: No. 2965 Longcheng Rd. Luoxi Town Xinbei District ChangZhou>

*This report is instead of SBRTC-2023-0612-1

Page 1 of 8

SHANGHAI BIOMATERIALS RESEARCH & TEST CENTER

Add: 201, Building 2, № 427 Jumen Road, Shanghai, China

Zip Code: 200023

TEL: 0086-21-63034903

FAX: 0086-21-63011643

Web site: www.sbrtc.com

E-mail: biomatercenter@163.com

NOTICE

1. It will be invalid for the report without a connective seal.
2. It will be invalid for the report without the signature of study director.
3. It will be invalid for the manual revision of the report.
4. This English report "SBRTC-2023-0612-1" was replaced by "SBRTC-2023-0612-4". According to the requirement of the sponsor, the name of Manufacturer and Sponsor were modified in the reports because of the mistake in the client's contract.
5. It can't be copied partly on the report without agreement, nor can be as the recorder of the order receiving and advertisement registration.
6. Please raise the objection to the Center within 15 days after the receipt of the report, otherwise it will be considered to accept the testing result.
7. It is only responsible for the samples received.

*This report is instead of SBRTC-2023-0612-1

Page 2 of 8

SHANGHAI BIOMATERIALS RESEARCH & TEST CENTER

Add: 201, Building 2, № 427 Jumen Road, Shanghai, China

Zip Code: 200023

TEL: 0086-21-63034903

FAX: 0086-21-63011643

Web site: www.sbrtc.com

E-mail: biomatercenter@163.com

TABLE OF CONTENTS

SUMMARY4

INTRODUCTION.....5

MATERIALS.....5

METHODS.....6

DEVIATIONS7

RESULTS.....7

CONCLUSION.....7

RECORD STORAGE.....7

PHOTOGRAPH OF THE TEST ARTICLE.....8

*This report is instead of SBRTC-2023-0612-1

SUMMARY

An in vitro cytotoxicity study was conducted to assess the potential for cytotoxicity of the test article, **Medical endoscope insertion tube**, based on the International Organization for Standardization ISO 10993-5:2009 Biological evaluation of medical devices - Part 5: Tests for in vitro cytotoxicity; ISO 10993-12:2021 Biological evaluation of medical devices - Part 12: Sample preparation and reference materials.

Four concentrations (100%, 75%, 50%, and 25%) of the test sample extracts, the blank, 100% of the negative control and the positive control were prepared using Minimum Essential Medium (MEM) supplemented with 10% fetal bovine serum. The semi-confluent monolayers of L-929 mouse fibroblast cells were incubated with the test extract, the blank and other two controls, supplemented with 10% fetal bovine serum in a 96-well microplate respectively at 37°C under the condition of 5% CO₂. At 24h, the MTT colorimetric assay was employed and the plate was read on a microplate reader at 570 and 650 nm. The viability of the cells was calculated.

Under the condition of this study, the viability of 100% extract of the test sample was 74%. It can be considered that the test sample extracts had not a cytotoxic potential.


Study and Supervisory

Personnel: JI Lina

HUANG Zhewei

Study Director:


SUN Jiao, Ph.D.


Date Completed

INTRODUCTION

The study was performed in order to determine whether leachables extracted from the test article would cause cytotoxicity. This test was conducted based on the requirements of ISO 10993-5:2009 Biological evaluation of medical devices - Part 5: Tests for *in vitro* cytotoxicity. The test article was received on Jul. 13, 2023. The cells were first exposed to the extract on Aug. 24, 2023, and the final observations were concluded on Aug. 25, 2023.

This study was completed in the Lab of Shanghai Biomaterials Research & Test Center (SBRTC). SBRTC was conducted in accordance with the provisions of the ISO/IEC 17025: 2017.

MATERIALS

The test article provided by the sponsor was identified and handled as follows:

Test Article:	Medical endoscope insertion tube <Production date: 2023.7.1; Lot : 230701>
Identification №:	230720
Sterilization Status:	Non Sterile
Storage Temperature:	Room temperature
Extraction Vehicle:	gibco's Minimum Essential Medium (2395101) supplemented with L-glutamine and 10% fetal bovine serum (BG9605)
Test Extract Preparation:	According to the requirement of the sponsor, the test samples were cut into small pieces and sterilized at 121 °C for 30min before testing. Based on the ISO 10993-12:2021, the ratio of 0.2g/ml [Weight of the test sample to volume of extraction vehicle] was adopted for testing. 3g of the test samples (Sampling according to the statement of the sponsor) were submersed in 15ml of extraction vehicle under aseptic conditions for preparing the test extract at 37°C for 24 hours with continuously agitation during extraction. The extract was used immediately after extraction.
Blank Preparation:	The extraction vehicle not containing the test sample, retained in a vessel identical to that which holds the test sample and subjected to conditions identical to those to which the test sample is subjected during its extraction.
Negative Control Preparation :	High-density polyethylene film (221026), which was current SBRTC negative control (having been demonstrated to be noncytotoxicity) coming from Hatano Research Institute, FDSC. The ratio of 3cm ² /ml [surface area of the test sample to volume of extraction vehicle] was used and extracted at 37°C for 24 h.

Positive Control Preparation: Polyurethane film containing 0.1% zinc diethyldithiocarbamate (ZDEC) (221028) which was current SBRTC positive control (having been demonstrated to be severe cytotoxicity) coming from Hatano Research Institute, FDSC. The ratio of $6\text{cm}^2/\text{ml}$ [surface area of the test sample to volume of extraction vehicle] was used and extracted at 37°C for 24 h.

Condition of Extracts: All the extracts of the test samples and the controls were clear, no suspended particulates and without any special treatments.

METHODS

Test System Management:

Mouse fibroblast cells (L 929, from the cell bank of Shanghai Institutes for Biological Sciences), were cultured in MEM supplemented with L-glutamine and 10% fetal bovine serum at 37°C in a gaseous environment of 5% carbon dioxide (CO_2). A 96-well microplate method was employed for the MTT colorimetric assay. Each well was seeded $100\mu\text{l}$ suspension of 1×10^4 cells, and incubated at 37°C in 5% CO_2 atmosphere for 24h prior to use.

Experimental Procedure:

After incubation, the growth medium was replaced with $100\mu\text{l}$ four concentrations (100%, 75%, 50% and 25%) of the test extract, 100% of the negative control and the positive control, the blank (row 2 and 11) respectively. Six replicates were prepared for each group. The 96-well plate were incubated at 37°C in 5% CO_2 for 24h.

After 24 h treatment, the culture medium was removed carefully from the plates. $50\mu\text{l}$ of the MTT (1mg/mL) solution was then added to each test well and the plates were further incubated for 2 h at 37°C in a 5% CO_2 atmosphere. Then the MTT solution was removed and $100\mu\text{l}$ isopropanol per well was added and shake for 10min by gently. The plate was read on a microplate reader at 570 nm (reference wavelength 650 nm). The viability of the cells was calculated according to the formula below:

$$\text{Viab. \%} = \frac{100 \times OD_{570e}}{OD_{570b}}$$

Where

OD_{570e} is the mean value of the measured optical density of the extracts of the test sample;

OD_{570b} is the mean value of the measured optical density of the blanks;

A test meets acceptance criteria if the left and the right mean of the blanks do not differ by more than 15% from the mean of all blanks. If the viability of the test sample was reduced to <70% of the blank, it had a cytotoxic potential. The 50% extract of the test sample should have at least the same or a higher viability than the 100% extract; otherwise the test should be repeated.

DEVIATIONS

There were no deviations from the ISO 10993-5:2009.

RESULTS

Group	1	2	3	4	5	6	The optical density (570nm–650 nm)	Viab . %
100% of the negative control	0.875	0.861	0.839	0.837	0.858	0.777	0.841±0.035	100
100% of the test extract	0.654	0.618	0.602	0.659	0.608	0.605	0.624±0.026	74
75% of the test extract	0.633	0.704	0.693	0.653	0.648	0.618	0.658±0.034	78
50% of the test extract	0.652	0.688	0.674	0.698	0.687	0.712	0.685±0.021	81
25% of the test extract	0.747	0.711	0.715	0.722	0.759	0.749	0.734±0.020	87
100% of the positive control	0.035	0.034	0.033	0.031	0.031	0.032	0.033±0.002	4
The blank (row 2)	0.792	0.866	0.867	0.868	0.893	0.807	0.849±0.040	/
The blank (row 11)	0.872	0.804	0.878	0.805	0.817	0.851	0.838±0.033	/

Note: n=6

The mean value of optical density of the blank was 0.843 ± 0.036 . Both the left (row 2) and the right (row 11) mean of the blanks were less than 15% from the mean of all blanks.

Results and conclusions apply only to the test article tested. No further evaluation of these results was made by Shanghai Biomaterials Research & Test Center.

CONCLUSION

Under the condition of this study, the viability of 100% extract of the test sample was 74%. It can be considered that the test sample extracts had not a cytotoxic potential.

RECORD STORAGE

All raw data pertaining to this study and a copy of the final report are to be stored in the designated archive files at Shanghai Biomaterials Research & Test Center.

PHOTOGRAPH OF THE TEST ARTICLE



*This report is instead of SBRTC-2023-0612-1

Page 8 of
8

SHANGHAI BIOMATERIALS RESEARCH & TEST CENTER

Add: 201, Building 2, № 427 Jumen Road, Shanghai, China

Zip Code: 200023

TEL: 0086-21-63034903

FAX: 0086-21-63011643

Web site: www.sbrtc.com

E-mail: biomatercenter@163.com